

Tubing OD, in	BWG gauge	Wall thickness, in	Inside cross- sectional area, in ²	Ft ² external surface per ft length	Ft ² internal surface per ft length	Weight per ft length steel, lb †	Tubing ID, in	Moment of inertia, in ⁴	Section modulus, in ³	Radius of gyration, in	Costant C ‡	OD ID	Transverse metal area, in ²
1/4	22	0.028	0.0295	0.0655	0.0508	.0066	0.194	0.00012	0.00098	0.0792	46	1.289	0.0195
1/4	24	.022	.0333	.0655	.0539	.054	.206	.00011	.00083	.0810	52	1.214	.0159
1/4	26	.018	.0360	.0655	.0560	.045	.214	.00009	.00071	.0824	56	1.168	.0131
1/4	27	.016	.0373	.0655	.0570	.040	.218	.00008	.00064	.0829	58	1.146	.0117
3/8	18	.049	.0603	.0982	.0725	.171	.277	.00068	.0036	.1164	94	1.354	.0502
3/8	20	.035	.0731	.0982	.0798	.127	.305	.00055	.0029	.1213	114	1.233	.0374
3/8	22	.028	.0799	.0982	.0835	.104	.319	.00046	.0025	.1227	125	1.176	.0305
3/8	24	.022	.0860	.0982	.0867	.083	.331	.00038	.0020	.1248	134	1.133	.0244
1/2	16	.065	.1075	.1309	.0969	.302	.370	.0022	.0086	.1556	168	1.351	.0888
1/2	18	.049	.1269	.1309	.1052	.236	.402	.0018	.0072	.1606	198	1.244	.0694
1/2	20	.035	.1452	.1309	.1126	.174	.430	.0014	.0056	.1649	227	1.163	.0511
1/2	22	.028	.1548	.1309	.1162	.141	.444	.0012	.0046	.1671	241	1.126	.0415
5/8	12	.109	.1301	.1636	.1066	.602	.407	.0061	.0197	.1864	203	1.536	.177
5/8	13	.095	.1486	.1636	.1139	.537	.435	.0057	.0183	.1903	232	1.437	.158
5/8	14	.083	.1655	.1636	.1202	.479	.459	.0053	.0170	.1938	258	1.362	.141
5/8	15	.072	.1817	.1636	.1259	.425	.481	.0049	.0156	.1971	283	1.299	.125
5/8	16	.065	.1924	.1636	.1296	.388	.495	.0045	.0145	.1993	300	1.263	.114
5/8	17	.058	.2035	.1636	.1333	.350	.509	.0042	.0134	.2016	317	1.228	.103
5/8	18	.049	.2181	.1636	.1380	.303	.527	.0037	.0118	.2043	340	1.186	.089
5/8	19	.042	.2298	.1636	.1416	.262	.541	.0033	.0105	.2068	358	1.155	.077
5/8	20	.035	.2419	.1636	.1453	.221	.555	.0028	.0091	.2089	377	1.126	.065
3/4	10	.134	.1865	.1963	.1262	.844	.482	.0129	.0344	.2229	285	1.556	.260
3/4	11	.120	.2043	.1963	.1335	.809	.510	.0122	.0326	.2267	319	1.471	.238

3/4	12	.109	.2223	.1963	.1393	.748	.532	.0116	.0309	.2299	347	1.410	.220
3/4	13	.095	.2463	.1963	.1466	.666	.560	.0107	.0285	.2340	384	1.339	.196
3/4	14	.083	.2679	.1963	.1529	.592	.584	.0098	.0262	.2376	418	1.284	.174
3/4	15	.072	.2884	.1963	.1587	.520	.606	.0089	.0238	.2410	450	1.238	.153
3/4	16	.065	.3019	.1963	.1623	.476	.620	.083	.0221	.2433	471	1.210	.140
3/4	17	.058	.3157	.1963	.1660	.428	.634	.0076	.0203	.2455	492	1.183	.126
3/4	18	.049	.3339	.1963	.1707	.367	.652	.0067	.0178	.2484	521	1.150	.108
3/4	20	.035	.3632	.1963	.1780	.269	.680	.0050	.0134	.2532	567	1.103	.079
7/8	10	.134	.2892	.2291	.1589	1.061	.607	.0221	.0505	.2662	451	1.441	.312
7/8	12	.109	.3390	.2291	.1720	.891	.657	.0196	.0449	.2736	529	1.332	.262
7/8	13	.095	.3685	.2291	.1793	.792	.685	.0180	.0411	.2778	575	1.277	.233
7/8	14	.083	.3948	.2291	.1856	.704	.709	.0164	.0374	.2815	616	1.234	.207
7/8	16	.065	.4359	.2291	.1950	.561	.745	.0137	.0312	.2873	680	1.174	.165
7/8	18	.049	.4742	.2291	.2034	.432	.777	.0109	.0249	.2925	740	1.126	.127
7/8	20	.035	.5090	.2291	.2107	.313	.805	.0082	.0187	.2972	749	1.087	.092
1	8	.165	.3526	.2618	.1754	1.462	.670	.0392	.0784	.3009	550	1.493	.430
1	10	.134	.4208	.2618	.1916	1.237	.732	.0350	.0700	.3098	656	1.366	.364
1	11	.120	.4536	.2618	.1990	1.129	.760	.0327	.0654	.3140	708	1.316	.332
1	12	.109	.4803	.2618	.2047	1.037	.782	.0307	.0615	.3174	749	1.279	.305
1	13	.095	.5153	.2618	.2121	.918	.810	.0280	.0559	.3217	804	1.235	.270
1	14	.083	.5463	.2618	.2183	.813	.834	.0253	.0507	.3255	852	1.199	.239
1	15	.072	.5755	.2618	.2241	.714	.856	.0227	.0455	.3291	898	1.167	.210
1	16	.065	.5945	.2618	.2278	.649	.870	.0210	.0419	.3314	927	1.149	.191
1	18	.049	.6390	.2618	.2361	.496	.902	.0166	.0332	.3366	997	1.109	.146
1	20	.035	.6793	.2618	.2435	.360	.930	.0124	.0247	.3414	1060	1.075	.106
1 1/4	7	.180	.6221	.3272	.2330	2.057	.890	.0890	.1425	.3836	970	1.404	.605

1 1/4	8	.165	.6648	.3272	.2409	1.921	.920	.0847	.1355	.3880	1037	1.359	.565
1 1/4	10	.134	.7574	.3272	.2571	1.598	.982	.0741	.1186	.3974	1182	1.273	.470
1 1/4	11	.120	.8012	.3272	.2644	1.448	1.010	.0688	.1100	.4018	1250	1.238	.426
1 1/4	12	.109	.8365	.3272	.2702	1.329	1.032	.0642	.1027	.4052	1305	1.211	.391
1 1/4	13	.095	.8825	.3272	.2775	1.173	1.060	.0579	.0926	.4097	1377	1.179	.345
1 1/4	14	.083	.9229	.3272	.2838	1.033	1.084	.0521	.0833	.4136	1440	1.153	.304
1 1/4	16	.065	.9852	.3272	.2932	.823	1.120	.0426	.0682	.4196	1537	1.116	.242
1 1/4	18	.049	1.042	.3272	.3016	.629	1.152	.0334	.0534	.4250	1626	1.085	.185
1 1/4	20	.035	1.094	.3272	.3089	.456	1.180	.0247	.0395	.4297	1707	1.059	.134

1 1/2	10	.134	1.192	.3927	.3225	1.955	1.232	.1354	.1806	.4853	1860	1.218	.575
1 1/2	12	.109	1.291	.3927	.3356	1.618	1.282	.1159	.1546	.4933	2014	1.170	.476
1 1/2	14	.083	1.398	.3927	.3492	1.258	1.334	.931	.1241	.5018	2181	1.124	.370
1 1/2	16	.065	1.474	.3927	.3587	.996	1.370	.0756	.1008	.5079	2299	1.095	.293

2	11	.120	2.433	.5236	.4608	2.410	1.760	.3144	.3144	.6660	3795	1.136	.709
2	14	.038	9	.5236	.4801	1.699	1.834	.2300	.2300	.6784	4121	1.090	.500

2 1/2	9	.148	3.815	.6540	.5770	3.719	2.204	.7592	.6074	.8332	5951	1.134	1.094
-------	---	------	-------	-------	-------	-------	-------	-------	-------	-------	------	-------	-------

† Weights are based on low-carbon steel with a density of 0.2833 lb/in³. For other metals multiply by the following factors:

Aluminum.....0.35	Aluminum brass.....1.06
Titanium.....0.58	Nickel-chrome-iron.....1.07
AISI 400 series stainless steels...0.99	Admiralty.....1.09
AISI 300 series stainless steels...1.92	Nickel and nickel-copper.....1.13
Aluminum bronze.....1.04	Copper and cupronickels....1.14

‡ Liquid velocity = (lb per tube per h / C x sp gr of liquid) in ft / s [sp gr of water at 16°C (60°F) = 1.0]